

## TRAIDAMID® G MoS<sub>2</sub> (PA6 C + MoS<sub>2</sub>)

Density 1,15 g/cm<sup>3</sup>  
Colour Black opaque  
Chemical Designation PA6 C ( Cast polyamide 6)

PROPERTIES	RESULT	UNIT	PARAMETER	NORM USED
<b>Mechanical properties</b>				
Modulus of elasticity	3200	MPa	1 mm/min	DIN EN ISO 527-2
Tensile strength	82	MPa	50 mm/min	DIN EN ISO 527-2
Tensile strength at yield	80	MPa	50 mm/min	DIN EN ISO 527-2
Elongation at yield	4	%	50 mm/min	DIN EN ISO 527-2
Elongation at break	55	%	50 mm/min	DIN EN ISO 527-2
Flexural strength	102	MPa	2 mm/min , 10 N	DIN EN ISO 178
Modulus of elasticity (flex test)	3000	MPa	2 mm/min , 10 N	DIN EN ISO 178
Compression strength	22 / 38	MPa	1% / 2%. 5 mm/min , 10 N	EN ISO 604
Compression modulus	2800	MPa	5 mm/min , 10 N	EN ISO 604
Impact strength (Charpy)	No break	Kj/m <sup>2</sup>	Max. 7,5j	DIN EN ISO 179-1EU
Notched Impact stren. (Charpy)	4	Kj/m <sup>2</sup>	Max. 7,5j	DIN EN ISO 179-1EU
Ball indentation hardness	170	MPa		ISO 2039-1
<b>Thermal properties</b>				
Glass transition temperature	43	°C		DIN 53765
Melting temperature	217	°C		DIN 53765
Service temperature	170	°C	Short term	
Service temperature	100	°C	Long term	
Thermal expansion	11	10 <sup>-5</sup> K <sup>-1</sup>	23-60°C long	DIN EN ISO 11359-1;2
Thermal expansion	11	10 <sup>-5</sup> K <sup>-1</sup>	23-100°C long	DIN EN ISO 11359-1;2
Specific heat	1,6	J/(g.K)		ISO 22007-4:2008
Thermal conductivity	0,33	W/(K.m)		ISO 22007-4:2008
<b>Electrical properties</b>				
Surface resistance	> 10 <sup>12</sup>	Ω		DIN IEC 60093
<b>Miscellaneous properties</b>				
Water absorption	0,2 / 0,5	%	24h / 96h (23°C)	DIN EN ISO 62
Resistance to hot mater / bases	(+)			
Resistance to weathering	(+)			
Flammability (UL94)	HB		According to	DIN IEC 60995-11-10

### MAIN CHARACTERISTICS

High strength  
Resistant to many greases, oils and fuels  
High toughness  
Good slide and wear resistance  
Good wear properties

### INDUSTRY APPLICATIONS

Heavy duty industry  
Conveyor technology  
Textile industry  
Mechanical engineering  
Engine manufacturing

Notice: The information given was made with our knowledge indicating our product's possible applications. Existing commercial patents must be observed. These values represent averages taken from samples, so we reserve the right of technical alterations. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.traidvillarroya.com](http://www.traidvillarroya.com). Traidamid, TKG and TVH as well as their logos are registered trademarks of the Traid Villarroya group of companies, in Europe and other countries.