

EPDM 100

Description	Standard	Value	Unit
Density	ISO 845	100	Kg/m ³
Tensile strength	ISO 1798	733	KPa
Elongation	ISO 1798	281	%
Compression 10%	ISO 844	32	kPa
Compression 25%	ISO 844	57	kPa
Compression 50%	ISO 844	132	kPa
Working temp. range	Internal	-60/80	°C
Water absorption Vol. (max.)	Internal	1	%
Shore	ISO 868	14	A

Last Update: March 2016

Palfoam is a closed cell cross-linked polyethylene foam block.
 Tolerances other than the above may be negotiated.
 If holes were created during the foaming process, no more than 5 holes of diameter 2mm per 1m² sheet are acceptable.
 This information on Palfoam chemically cross-linked polyethylene foam is presented to the best of our knowledge.
 Data represents typical values measured on a 10 mm thick specimen and should be considered as a guideline only.